

BH

(12) **UK Patent Application** (19) **GB** (11) **2 141 360 A**

(43) Application published 19 Dec 1984

(21) Application No 8413519

(22) Date of filing 25 May 1984

(30) Priority data

(31) 8314789
8317906

(32) 27 May 1983
1 Jul 1983

(33) GB

(71) Applicant

David Bradley Taylor,
44 Ravelston Dykes, Edinburgh EH 3JB

(72) Inventor

David Bradley Taylor

(74) Agent and/or Address for Service

J. Y. & G. W. Johnson,
Furnival House, 14-18 High Holborn, London WC1V 6DE

(51) INT CL³

B32B 15/00 B05D 5/00 B32B 27/30

(52) Domestic classification

B2E 1748 410S 418T 494T 506S M

C7B 120 124 712 PC

U1S 1022 1198 B2E C7B

(56) Documents cited

GB 1453578

GB 1366417

GB 1423578

GB 1046511

GB 1420339

GB 0794351

GB 1366444

(58) Field of search

B2E

(54) Means for reducing environmental pollution and toxicity from lead articles

(57) A lead article, e.g. lead shot or lead weight, coated with a coherent, wear-resistant coating of non-toxic but soft material, e.g. a solid film lubricant.

GB 2 141 360 A

SPECIFICATION

Means for reducing environmental pollution and toxicity from lead articles

5

The present invention relates to means for reducing environmental pollution and toxicity from lead articles, especially lead articles, used in field sports, such as lead shots and lead weights used in fishing.

10 For the sake of clarity in this specification the term "lead article(s)" is intended to embrace any article(s) made entirely or partly of lead and/or a lead alloy.

Large quantities of lead shot are used in game shooting and some remain embedded within the
15 game shot, whilst considerable lead shot waste (up to 95% and more) remains on the ground at the end of the shoot. Large quantities of lead weights used in fishing also remain in river beds. All these are sources of lead pollution in water and foods and
20 recent medical evidence has emphasised the potential hazards to health of lead pollution which may be caused by the weathering of exposed lead articles leading to formation of soluble lead compounds.

Attempts have been made to overcome the pollution hazards of lead shot and lead weights by
25 replacing the lead with an alternative material, especially steel. However steel shot is not satisfactory as it is too hard (Mohs hardness 5 to 8.5) and thus is prone to ricocheting and, when impacting a quarry, does not flatten but tends to pass right
30 through the quarry. Furthermore steel shot tends to rust, so that in damp conditions the individual pellets can become bonded together. Lead, by contrast, is corrosion-resistant, soft (Mohs hardness 1.5) and
35 readily fusible, and also dense, and there is no other material possessing such an attractive combination of properties.

It has also been proposed to coat lead shot with a substantial nickel coating but this also is unsatisfactory because it makes the shot very hard (Mohs
40 hardness of nickel approximately 6) and markedly affects the spreading characteristics. Thus, nickel-coated lead shot tends to pass through the quarry, which makes its use less humane. In addition, nickel
45 is very expensive. Accordingly, the use of such shot is restricted to shooting at "on edge" clay targets.

The present invention seeks to provide an alternative means for reducing the harm to the environment and toxic hazards stemming from ordinary lead shot,
50 lead weights and other lead articles without adversely affecting the good properties of these articles to a significant extent.

According to the invention there is provided a lead article, as hereinbefore defined, which is coated with
55 a coherent, wear-resistant coating of non-toxic but soft material.

It is essential according to the invention that the coating should be coherent (continuous), so that lead is not directly exposed to the ambient atmosphere, and that it should be sufficiently wear-resistant that it is not worn away in normal use of the
60 article, so as to expose the underlying lead, although it need not be fully abrasion-resistant to very hard abrasives. It is also necessary that the coating
65 material should not be toxic or cause environmental

pollution. Preferably the coating material should be sufficiently inert that it does not react chemically to any appreciable extent with materials with which it comes into contact during use of the lead article, as
70 this would tend to expose the underlying lead.

It is a further characterising feature of the coating material that it should be soft. Preferably, it will be softer than lead, although it may have a comparable or even a slightly greater hardness (Mohs hardness
75 up to about 2 or even about 3) than lead. Certainly, however, it must not be substantially harder than lead otherwise the benefit of the softness of lead will be lost entirely.

Another preferred feature for the coating is
80 reasonable heat-stability, at least up to 100°C and preferably up to 250°C for lead shot and the like, so that a lead article embedded in foodstuff is unaffected when the foodstuff is cooked.

One class of material capable of satisfying the
85 requirements for the coating material are to be found amongst solid-film lubricants, especially molybdenum disulphide and polytetrafluoroethylene, both of which have proved to be very satisfactory for the covering of lead shot, lead
90 weights and the like.

The coating materials may be applied to the lead shot in any convenient manner, for example by a dip or barrel spray process, normally with the aid of an appropriate adhesive resin, followed by drying in
95 such a way that a coherent (continuous) film is formed but there is no undesired adhesion, e.g. between individual lead shots. The coating need not be thick and thicknesses of 0.01 to 0.02 mm are satisfactory. If desired, more than one coating may
100 be applied. A heat-curing stage may be employed, where appropriate, to improve the wear resistance of the coating.

The coatings may conveniently be composed of 25 to 95% by weight of molybdenum disulphide,
105 polytetrafluoroethylene or the like bonded with an adhesive resin and such coatings are heat-stable at temperatures up to 280°C.

Such coatings do not affect the spreading power of lead shot to which they have been applied.
110 Examination of such coated shot fired from a shotgun at a steel plate has shown that the coating does not flake off although it may become crazed under these severe and unusual conditions. Further, the coated shot has excellent weathering properties
115 whilst undamaged and even the small proportion of used lead shot which has been damaged during use is likely to be considerably more weather-resistant than uncoated shot. Accordingly, considerable reductions in lead pollution are to be expected from
120 using the coated shot.

The coatings proposed also have a long life-expectancy and high load-bearing capacity and are dirt-resistant, as well as being easily applied.

Another coating material which is satisfactory is
125 aluminium. This may be applied by any convenient method to the lead article, e.g. lead shot or a lead fishing weight. One suitable method is the electrolytic process known as the "siegel" process which enables a thin, non-poisonous, weather-resistant
130 coating to be deposited, which is both soft and

ductile so that it will deform with the lead shot on impact and will tend not to flake off. The coating may be extremely thin (e.g. several μm or even less) or may be thicker (e.g. up to 0.02 mm). Although the coating produced is corrosion-resistant, additional corrosion resistant can be imparted by anodising the coating, and this anodising can be of any colour for identification purposes.

It will be appreciated that aluminium is harder than lead although it is a relatively soft metal in its pure state. Aluminium is softer, for example, than copper (Mohs hardness of approximately 3).

CLAIMS

1. A lead article, as hereinbefore defined, which is coated with a coherent, wear-resistant coating of non-toxic but soft material.
2. A lead article according to claim 1, in which the coating material has a Mohs hardness of 3 or less.
3. A lead article according to claim 1 or 2, in which the coating material is reasonably heat-stable at least up to 100°C.
4. A lead article according to claim 3, in which the coating material is reasonably heat stable at least up to 250°C.
5. A lead article according to any of the preceding claims, in which the coating has a thickness no greater than 0.02 mm.
6. A lead article according to any of the preceding claims, in which the coating material is inert.
7. A lead article according to any of the preceding claims, in which the coating material comprises a solid film lubricant.
8. A lead article according to claim 7, in which the coating material comprises molybdenum disulphide.
9. A lead article according to claim 7, in which the coating material comprises polytetrafluoroethylene.
10. A lead article according to any of the preceding claims, in which the coating material is bonded to the lead article with an adhesive resin.
11. A lead article according to any of claims 1 to 5, in which the coating material comprises a metal deposited on the lead by electrolysis.
12. A lead article according to claim 11, in which the coating material comprises aluminium.
13. A lead article according to claim 11 or 12, in which the electroplated layer has a thickness no greater than several μm .
14. A lead article according to any of the preceding claims, in the form of lead shot.
15. A lead article according to any of claims 1 to 13, in the form of a lead weight.
16. A lead article, as hereinbefore defined, which is coated with a coherent, wear-resistant layer of protective material, the layer having a thickness no greater than 0.02 mm.

17. A lead article, as hereinbefore defined, constructed and arranged substantially as herein described.

Printed in the UK for HMSO, D8818935, 10/84, 7102.
Published by The Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from which copies may be obtained.